

# Li2000 Thermal Tape



## Features


- Silicone PSA
- Short time use temperature of 288°C
- Long time use temperature of 170°C
- UL compliant
- Electrical insulation

## Applications

- Electronic components: IC, CPU, MOS
- LED, M/B, P/S, Heat Sink,
- LCD-TV, Notebook PC, PC, Telecom Device, Wireless Hub.....e
- DDR II Module, DVD Applications, Hand-set applications.....e

## Properties


- ✓ REACH Compliant
- ✓ RoHS Compliant
- ✓ UL Compliant




Thermal Conductivity: 1.2 W/m.K (W/m.K, Z ax

Physical Properties	Li2000		Unit	Tolerance	Test Method
Thermal Conductivity	1.2	1.2	W / mK	±0.12	ASTM D5470
Thickness	0.15	0.25	mm	-	ASTM D374
Color	White	White	-	-	Visual
Reinforcement Carrier	Fiberglass		-	-	-
Continuous Working Temperature	-45~170	-45~170	°C	-	-
Short time Use Temperature (30sec)	288	288	°C	-	-
Density	1.6	1.6	g / cm <sup>3</sup>	-	ASTM D792
Initial Tack	10	10	cm	-	PSTC-6
Lap Shear Strength	74	76	N / cm <sup>2</sup>	-	D1002
Die Shear Strength @25°C	113	126	N / cm <sup>2</sup>	-	-
Die Shear Strength @80°C	80	85	N / cm <sup>2</sup>	-	-
Die Shear Strength @150°C	30	35	N / cm <sup>2</sup>	-	-
Holding Power 1000g@25°C using 1 in <sup>2</sup>	>40000	>40000	min	-	PSTC-7
Holding Power 1000g@80°C using 1 in <sup>2</sup>	>40000	>40000	min	-	PSTC-7
Holding Power 1000g@150°C using 1in <sup>2</sup>	>10000	>10000	min	-	PSTC-7
Tensile Strength	450	650	psi	-	ASTM D412
Dielectric Breakdown Voltage(Vac)	2	3	KV	±10%	ASTM D149
Dielectric Breakdown Voltage (Vdc)	3	4	KV	±10%	ASTM D149
Volume Resistance	>10 <sup>11</sup>	>10 <sup>11</sup>	Ohm-cm	-	ASTM D257
Thermal Impedance@ 10psi	0.70	1.17	°C-in <sup>2</sup> / W	-	ASTM D5470
Thermal Impedance@ 30psi	0.68	1.13	°C-in <sup>2</sup> / W	-	ASTM D5470
Thermal Impedance@ 50psi	0.63	1.07	°C-in <sup>2</sup> / W	-	ASTM D5470
Flame Rating	V-0	V-0	-	-	UL 94

Need Samples?



Pre-cut for different shapes



1. Choose the P/N
2. Fill into size: x, y, z
3. Fill the quantity you need

T-Global Technology Co., Ltd

No. 33, Ln. 50, Daren Rd., Taoyuan Dist., Taoyuan City 330, Taiwan

TEL: +886-3-3618899

www.tglobalthermal.com

FAX: +886-3-3665666

www.tglobal.com.tw

Thermal Interface Materials: Thermal Pad, Thermal Tape, Thermal Grease, Ceramic Heat Spreader



Version3 20160226